

### **Maximum Velocity & Perfomance**


APPLICATIONS
ATHLETIC FIELDS
GOLF COURSES

**LANDSCAPE** 











**J-DRAIN MVP** is a 3-dimensional, high-flow, polyethylene/polypropylene blend drainage core which is wrapped with either non-woven filter fabric (MVP I) or spun-bounded filter fabric(MVP II). It is designed to retain soil particles while allowing water to pass through the drain core for easy removal of water. **J-DRAIN MVP-6** is placed vertically in narrow, less intrusive trenches and sloped to collection drains in natural turf applications. **J-DRAIN MVP-12** is placed horizontally across the field toward the sideline trench in synthetic turf applications.





NOTE: J-UKAIN MVP-12 is placed horizontally across playing field and sloped to sideline trenches thus eliminating cross field trenching.

### PHYSICAL PROPERTIES

ore

Compressive Strength (ASTMD-1621) Thickness (ASTM-1777) In-Plane Flow (ASTMD-4716) (Q&518 psf & Hydraulic gradient = .1) 12,500 psf (598 kN/m²) 1 ln. (2.54 cm.) 30 gpm/ft width (372 lpm/m)

Roll

Roll Weight: 38 or 68 lbs. (17 or 30.5 kgs.) Roll Width: 6",12",& 18" (15,30, & 45 cm.) Roll Length: 165 ft. (50.29 meters)

#### MVP | Black Non-Woven

Flow (ASTM D-4491)
CBR Puncture (ASTM D-6241)
AOS (ASTM D-4751)
Grab Tensile (ASTM D-4632)
Mullen Burst (ASTM D-3786)
U.V. Resistance (ASTM D-4355)

140 gpm/ft² (5704 lpm/m²) 250 lbs. (1.11 kN) 70 U.S. Sieve (.212 mm) 100 lbs. (.45 kN) 210 PSI (1447 KpA) 70% @500 hrs. MVP II Grey Spun-Bonded

95 gpm/ft² (3870 lpm/m²) 225 lbs. (1.0 kN) 50 U.S. Sieve (.30 mm) 110 lbs. (.495 kN) 90 PSI (620 KpA) 70% @500hrs.

The information contained herein is believed by JDR Enterprises, Inc. to be accurate and is offered solely for the customer's consideration, investigation and verification. Determination of suitability for use is the responsibility of the user. JDR's Limitiations, Limited Warranty, & Disclaimer along with Standard Terms & Conditions apply. See www.j-drain.com for more info. Limitations: J-DRain is resistant to chemicals in normal soil environments. However, some reagents may affect the performance of J-DRain. A JDR representative should be contacted for further information to determine the suitability of use of J-DRain in unusual soil environments. J-DRain should be limited to its exposure to ultra-violet sunlight. J-DRain should be backfilled or covered within seven days of installation. Disclaimer; All information, drawings and specifications are based on the latest published information at the time of printing, JDR reserves the right to make changes due to manufacturing improvements and engineering at any time. All physical properties are minimum average roll values (MARV). Standard variations of 10% in mechanical properties and 15% in hydraulic properties are normal.



# **Synthetic Turf Applications**

























## **Natural Turf Applications**

























