

Nonwoven Sediment Socks Specifications

DESCRIPTION: Nonwoven Sediment Sock shall consist of three parts:

1. Sediment Sock geotextile shall be a 36" needle punched, nonwoven filter fabric, machine produced from 100% polypropylene. Geotextile should be designed specifically to retain sediment and remain highly permeable to water. Desired characteristics include small pore size, high U.V. resistance, high permittivity and a high percent open area.
2. 13/4 Cotton or Polyester Thread

GEOTEXTILE PROPERTIES:

<u>Mechanical/ Physical Properties</u>	<u>Description/Minimum Average Roll Values</u>	<u>Test Method</u>
Structure	Nonwoven, needle punched	
Polymer	Polypropylene	
U.V. Resistance (@ 500hrs)	>70% Strength Retained	ASTM D4355
Permittivity	1.4 Sec ⁻¹	ASTM D4491
Flow Rate	105 gpm/ft ²	ASTM D4491
Grab Tensile Strength	160 lbs	ASTM D4632
Grab Tensile Elongation	50%	ASTM D4632
Trapezoid Tear Strength	60 lbs	ASTM D4533
AOS (U.S. Sieve)	#70 Sieve	ASTM D4751
CBR Puncture Strength	410 lbs	ASTM D6241
Color	<u>Black</u>	

ASSEMBLY:

Geotextile shall be sewn into tube.

PACKAGING:

Color:	Black
Tube Diameter	10" +/- 1"
Tube Length	10' +/- 3"
Laying Length	9' 6"
Weight/Tube	1lbs. +/-