

TENCATE GEOSYNTHETICS
Americas

www.drainagesolutionsinc.com

## Mirafi® HP270







Mirafi<sup>®</sup> HP270 geotextile is composed of high-tenacity polypropylene yarns, which are woven into a network such that the yarns retain their relative position. Mirafi<sup>®</sup> HP270 geotextile is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). NTPEP Listed

| Mechanical Properties                  | Test Method | Unit   | Minimum Average<br>Roll Value |             |
|--|-------------|--|-------------------------------|-------------|
|  |             |  | MD                            | CD          |
| Tensile Strength (at ultimate)         | ASTM D4595  | lbs/ft (kN/m)                                      | 2640 (38.5)                   | 2460 (35.9) |
| Tensile Strength (at 2% strain)        | ASTM D4595  | lbs/ft (kN/m)                                      | 504 (7.4)                     | 600 (8.8)   |
| Tensile Strength (at 5% strain)        | ASTM D4595  | lbs/ft (kN/m)                                      | 1272 (18.6)                   | 1440 (21.0) |
|  |             |  | Minimum Roll Value            |             |
| Flow Rate                              | ASTM D4491  | gal/min/ft <sup>2</sup><br>(l/min/m <sup>2</sup> ) | 40 (1630)                     |             |
| Permittivity                           | ASTM D4491  | sec <sup>-1</sup>                                  | 0.6                           |             |
|  |             |  | Maximum Opening Size          |             |
| Apparent Opening Size (AOS)            | ASTM D4751  | U.S. Sieve (mm)                                    | 30 (0.60)                     |             |
|  |             |  | Typical To                    | est Value   |
| Pore Size 0 <sub>95</sub> 1            | ASTM D6767  | microns  | 386                           |             |
| Pore Size 0 <sub>50</sub> <sup>1</sup> | ASTM D6767  | microns  | 295                           |             |
|  |             |  | Minimum Test Value            |             |
| Factory Sewn Seam                      | ASTM D4884  | lbs/ft (kN/m)                                      | 1260 (18.4)                   |             |
| UV Resistance (at 500 hours)           | ASTM D4355  | % strength retained                                | 80                            |             |

<sup>&</sup>lt;sup>1</sup> Based on Third Party Testing

| Physical Properties              | Unit     | Roll Size              |                         |
|----------------------------------|----------|------------------------|-------------------------|
| Roll Dimensions (width x length) | ft (m)   | 15 x 300<br>(4.5 x 91) | 17 x 375<br>(5.2 x 114) |
| Roll Area                        | yd² (m²) | 500 (418)              | 708 (592)               |

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi® is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

