

PRODUCT DATA SHEET

WINFAB 1200N









WINFAB 1200N is a needlepunched nonwoven geotextile manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position.

WINFAB 1200N resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D4632	300 x 300 lbs	1335 x 1335 N
Elongation	ASTM D4632	50%	50%
CBR Puncture	ASTM D6241	825 lbs	3670 N
Trapezoidal Tear	ASTM D4533	115 x 115 lbs	511 x 511 N
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D4751	100 US Std. Sieve	0.150 mm
Permittivity	ASTM D4491	1.0 sec ⁻¹	1.0 sec ⁻¹
Water Flow Rate	ASTM D4491	75 gpm/ft²	3055 lpm/m ²

^{*}Maximum Average Roll Valve

Notes:

- Mullen Burst ASTM D3786 has been removed. It is not recognized by ASTM D35 on Geosynthetics.
- Puncture ASTM D4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241

PROPERTY	Typical English	Typical Metric
Roll Dimensions	15 x 300 ft	4.6 x 91.5 m
Roll Area	500 yd ²	418 m²

Disclaimer: Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. Willacoochee Industrial Fabrics disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2016 Willacoochee Industrial Fabrics, Inc.



