

PRODUCT DATA SHEET

WINFAB 450N









WINFAB 450N is a needlepunched nonwoven geotextile manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position.

WINFAB 450N resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D-4632	120 x 120 lbs	534 x 534 N
Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	335 lbs	1490 N
Trapezoidal Tear	ASTM D-4533	50 x 50 lbs	222 x 222 N
UV Resistance (500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	70 US Std. Sieve	0.212 mm
Permittivity	ASTM D-4491	1.8 sec ⁻¹	1.8 sec ⁻¹
Water Flow Rate	ASTM D-4491	120 gpm/ft ²	4889 lpm/m ²

^{*}Maximum Average Roll Valve

Notes:

- Mullen Burst ASTM D-3786 has been removed. It is not recognized by ASTM D-35 on Geosynthetics.
- Puncture ASTM D-4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D-6241

PROPERTY	Typical English	Typical Metric
Roll Dimensions	12.5 x 360 ft 15 x 360 ft	3.81 x 109.8 m 4.6 x 109.8 m
Roll Area	500 yd² 600 yd²	418 m² 502 m²

Disclaimer: Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. Willacoochee Industrial Fabrics disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2013 Willacoochee Industrial Fabrics, Inc.



